
1 2 3 4 5 6 7 8

TECHNICAL SHEET


ROOF MEMBRANE METALDREN 450 g SD-EUV FOLIA 450GLPM ADHESIVE TAPE






Example of using the METALDREN 450 g roofing foil under the KJG FALZ roof covering.

Polyamide structured separation layer with vapourpermeable foil and self-adhesive foil in the overlap.





Polypropylene – laminate + multifilament

| Technical parameter | | | | | | | |
|----------------------------|---------------------------------------|--|--|--|--|--|--|
| Roll dimensions | 1,5 m x 25 l.m. = 37,5 m ² | | | | | | |
| Area weight | c.a. 450 g/m² | | | | | | |
| Reaction to fire | E | | | | | | |
| Vapour permeability | 3000 g/m²/24 hod. | | | | | | |
| Resistance to UV radiation | 4 months * | | | | | | |
| Weight | 16,875 kg | | | | | | |

^{*} UV stabilization even up to 4 months according to artificial aging carried out in the laboratory relating to the conditions of average sun exposure for the climate of Central Europe

| INDEX | CHANGE | | DATE | SIGNATURE | KJG QUALITY ® | Scan code for 3D model |
|-----------|--------------------------------------------------|--|------|-------------|---------------------------------------------|------------------------|
| MATE | MATERIAL BRAND W.C. | | | W.C. | WEIGHT kg | SCALE |
| SIZE, | SIZE, SEMI-FINISHED PRODUCTS | | | | | |
| AUXI | AUXILIARY EQUIPMENT | | | | STN STANDARD | SORTING NUMBER |
| ELAB | ELABORATED BY Ing. Kluska M. | | | NOTE | POSITION NUMBER | |
| TESTED BY | | | | | | |
| TECH | TECHNOLOGIST TECHNOLOGIST | | | OLD DRAWING | DRAWING NUMBER | |
| NAMI | NAME Roof membrane METALDREN 450 g adhesive tape | | | g | Number of sheets SD-EUV FOLIA 450GLPM Sheet | |

Created: 04.12.2025 04:45:32

Technical changes reserved

1 2 3 4 5 6 7 8