

TECHNICAL SHEET

ENKE TWO-COMPONENT PRIMER

Enke Betoncoat – Grundierung 2K is a reactive, double-component, solvent-free, epoxy-based prime coat that can also be used as a barrier against solvents and alkalis.

A thin, reactive primer with a low odour with very good wettability and penetration into the surface, and also with an excellent ability to fill the pores of all common building mineral substrates.

The primer can be easily sandblasted if necessary. For surface filling of cracks and holes, it is possible to create a repair mortar from Grundierung 2K and dry silica sand with the corresponding grain size. A grain size of 0.1 – 0.3 mm is sufficient for most unevennesses.

Grundierung 2K is also used as a barrier against solvents when joining and lining with Enkolit on insulating materials.

For non-alkali-stable gaskets, Grundierung 2K is used as protection against alkalis. When used as a protection against alkalis or solvents, Grundierung 2K must be sandblasted. For these purposes a grain size of 0.7 – 1.2 mm is required.

APPLICATION:



Technical parameter	
Form of components delivery A+B	both thin
Mixing ratio	7,5 hm T comp. A + 3,0 hm T comp. B
Small component container A+B	both thin
Mixing ratio	2,0 hm T comp. A + 0,8 hm T comp. B
Viscosity (A+B)	approx. 500 mPa s [20 °C]
Density (A+B)	approx. 1,1 g/cm³ [20 °C]
Time for processing	approx. 20 minutes [20 °C]
Application	roller or rubber spatula
Consumption	300 – 400 g/m² (according to the nature of the floor)
Component A	7,5 kg
Component B	3,0 kg

SCH-ENKE GR.2K A 7,5



INDEX	CHANGE	DATE	SIGNATURE	KJG QUALITY ©	
MATERIAL BRAND			W.C.	WEIGHT kg	SCALE
SIZE, SEMI-FINISHED PRODUCTS				STN STANDARD	SORTING NUMBER
AUXILIARY EQUIPMENT				NOTE	POSITION NUMBER
ELABORATED BY Ing. Kluska M.					
TESTED BY					
TECHNOLOGIST		TECHNOLOGIST		OLD DRAWING	DRAWING NUMBER
NAME Enke two-component primer				Number of sheets	SCH-ENKE GR.2K A 7,5 Sheet

Created: 19.04.2026 21:25:06

Technical changes reserved